

**WHAT IS CLAIMED IS:**

1. A nonwoven article comprising a plurality of intertwined fibers, wherein the density of the fibers in the nonwoven varies across the nonwoven article.
- 5 2. The nonwoven article according to Claim 1, wherein the nonwoven includes a first zone with a first density of the fibers therein, and a second zone with a second density of the fibers therein.
3. The nonwoven article according to Claim 2, wherein the first zone and the second zone are connected by the intertwining of the fibers between the  
10 first zone and the second zone.
4. The nonwoven article according to Claim 2, wherein the fibers forming the nonwoven comprise a plurality of high melt polyester fibers and a plurality of low melt polyester fibers.
5. The nonwoven article according to Claim 2, wherein the fibers forming  
15 the nonwoven comprise a plurality of high melt polyester fibers and a plurality of core sheath polyester fibers having a low melt polyester sheath.
6. The nonwoven article according to Claim 5, wherein the low melt polyester sheath has a melt temperature from about 110°C to about 180°C.
7. The nonwoven article according to Claim 5, wherein the core sheath  
20 polyester fibers comprise from about 40% to about 90% by weight of the fibers forming the nonwoven.
8. The nonwoven article according to Claim 5, wherein the high melt polyester fibers comprise from about 40% to about 10% by weight of the fibers forming the nonwoven.
- 25 9. The nonwoven article according to Claim 1, wherein the nonwoven includes a first zone with a first density of fibers therein, and a second zone in which the density of fibers therein varies across the second zone.

10. The nonwoven article according to Claim 9, wherein the first zone and the second zone are connected by the intertwining of the fibers between the first zone and the second zone.
11. The nonwoven article according to Claim 9, wherein the fibers forming the nonwoven comprise a plurality of high melt polyester fibers and a plurality of low melt polyester fibers.
12. The nonwoven article according to Claim 9, wherein the fibers forming the nonwoven comprise a plurality of high melt polyester fibers and a plurality of core sheath polyester fibers having a low melt polyester sheath.
13. The nonwoven article according to Claim 12, wherein the low melt polyester sheath has a melt temperature from about 110°C to about 180°C.
14. The nonwoven article according to Claim 12, wherein the core sheath polyester fibers comprise from about 40% to about 90% by weight of the fibers forming the nonwoven.
15. The nonwoven article according to Claim 12, wherein the high melt polyester fibers comprise from about 40% to about 10% by weight of the fibers forming the nonwoven.
16. The nonwoven article according to Claim 1, wherein the fibers forming the nonwoven comprise a plurality of high melt polyester fibers and a plurality of low melt polyester fibers.
17. The nonwoven article according to Claim 1, wherein the fibers forming the nonwoven comprise a plurality of high melt polyester fibers and a plurality of core sheath polyester fibers having a low melt polyester sheath.
18. The nonwoven article according to Claim 17, wherein the low melt polyester sheath has a melt temperature from about 110°C to about 180°C.

US PTO Customer No. 25280  
Case No. 2801

20. The nonwoven article according to Claim 17, wherein the high melt polyester fibers comprise from about 40% to about 10% by weight of the fibers forming the nonwoven.

5

[illegible]